

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank) 2. REPORT DATE 3. REPORT TYPE AND DATES COVERED
FINAL REPORT 01 Jul 93 - 30 Sep 96

4. TITLE AND SUBTITLE
(URIP-FY93) NONDESTRUCTIVE DETECTION AND CHARACTERIZATION OF CORROSION IN AIRCRAFT
5. FUNDING NUMBERS
61103D
3484/ES

6. AUTHOR(S)
Professor James H. Rose

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)
Center for Nondestructive Evaluation
Iowa State University
Ames, IA 50011
AFOSR-TR-96
0569

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)
AFOSR/NE
110 Duncan Avenue Suite B115
Bolling AFB DC 20332-8080
10. SPONSORING/MONITORING AGENCY REPORT NUMBER
9620-93-1-0439

11. SUPPLEMENTARY NOTES
19961206 193

12a. DISTRIBUTION/AVAILABILITY STATEMENT
APPROVED FOR PUBLIC RELEASE: DISTRIBUTION UNLIMITED
12b. DISTRIBUTION CODE

13. ABSTRACT (Maximum 200 words)
We have developed a fully characterized pulsed eddy current (PEC) instrument to detect and characterize "second-layer" corrosion in aircraft skin. In the first year, we developed the theory needed to accurately model the response of the PEC instrument measured on a variety of calibration specimens. In the second year, we made experimental measurements on a number of realistic samples including a corrosion test panel provided by Boeing corporation. In addition, inverse methods were developed for estimating the location and amount of hidden corrosion. In the third year, the inversion methods were fully incorporated in the PEC instrument. New methods were developed: (1) for calculating the response due to pitting corrosion; and (2) for removing interfering signals from fasteners and other structures. The experimental effort in the third year focused on technology transfer. The instrument was a highly successful participant in the Air Force blind trials for corrosion detection and characterization (carried out by ARINC corporation). The PEC instrument and its capability for the quantitative detection of hidden corrosion was demonstrated in visits to the Air Logistics Commands at McClellan, Kelly and Warner Robbins AFB's. Finally, the PEC instrument along with the quantitative analysis module was licensed to Sierra Matrix, Inc. of Fremont, California.

14. SUBJECT TERMS DTIC QUALITY INSPECTED 4 15. NUMBER OF PAGES
16. PRICE CODE
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED 18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED 19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED 20. LIMITATION OF ABSTRACT

Nondestructive Detection and Characterization of Corrosion in Aircraft

James H. Rose, John C. Moulder and Joseph N. Gray

Center for Nondestructive Evaluation

Iowa State University

Ames, IA 50011

Grant F49620-93-1-0439 P00002

Final Report:

Submitted Nov. 1996.

Objectives:

To detect and characterize corrosion in aircraft.

There are two inspection modalities being developed: pulsed eddy-currents and energy-resolved x-ray backscatter. Each modality has separate objectives:

Pulsed Eddy-Currents: To develop the theoretical and experimental basis needed for a fully characterized pulsed-eddy current (PEC) instrument to detect and characterize "second-layer" corrosion in aircraft skin. To develop the theoretical tools needed to detect and characterize corrosion in the second layer of aircraft skin using pulsed eddy-current measurements. To perform the experiments needed to validate the key insights developed in the theoretical effort.

Energy Resolved X-rays: To investigate the feasibility of novel x-ray based energy sensitive inspection and material characterization techniques for the detection and evaluation of the extent of hidden corrosion in aluminum aircraft structures. Special attention will be given to the development of an energy dispersive material characterization capability for single sided x-ray inspections.

Summary:

Pulsed Eddy-Currents:

We have developed a fully characterized pulsed eddy current (PEC) instrument to detect and characterize "second-layer" corrosion in aircraft skin. In the first year, we developed the theory needed to accurately model the response of the PEC instrument measured on a variety of calibration specimens. In the second year, we made experimental measurements on a number of realistic samples including a corrosion test panel provided by Boeing corporation. In addition, inverse methods were developed for estimating the location and amount of hidden corrosion. In the third year, the inversion methods were fully incorporated in the PEC instrument. New methods were developed: (1) for calculating the response due to pitting corrosion; and (2) for removing interfering signals from fasteners and other structures. The experimental effort in the third year focused on technology transfer. The instrument was a highly successful participant in the Air Force blind trials for corrosion detection and characterization (carried out by ARINC corporation). The PEC instrument and its capability for the quantitative detection of hidden corrosion was demonstrated in visits to the Air Logistics Commands at McClellan, Kelly and Warner Robbins AFB's. Finally, the PEC instrument along with the quantitative analysis module was licensed to Sierra Matrix, Inc. of Fremont, California.

Energy Resolved X-rays.

The activity over the last three years supported by the AFOSR in energy dispersive backscatter detection of corrosion in complex geometry's resulted in a number of advancements. The first year was devoted to developing a backscatter camera using CdTe detectors positioned in a ring around the incident beam. The initial design of the camera was for the use of an Am 241 isotope source. The final conclusion of the isotope source camera showed that these sources produce too little flux to acquire backscatter signals in a

reasonable time, i.e. less than one hour. The second year began by modifying the backscatter camera to accept an x-ray generator source. Bremsstrahlung sources are 10^4 times brighter than isotope sources. The modifications included a mounting mechanism and a beam monitor. The beam monitor is required as the intensity of typical x-ray tube sources fluctuates over time. The backscatter camera coupled to the tube source proved successful in measuring metal loss in several layers of aluminum skin. The backscatter signals from layered structures, especially when a rib and three or four skin layers, proved to be very complex. To interpret these signals we developed a model of the backscatter process. This model built on the previous base of x-ray radiography modeling developed at the Center for NDE at ISU. The backscatter model provides a means of understanding collimation, source/sample interaction and the effect of part geometry. To incorporate the complex part geometry's, we coupled the backscatter model to the CAD representation of the part geometry. The result, BKSIM, is a flexible backscatter model for determining the effect of scan parameters on the type and size of the backscatter signal. In the third year we began to develop an extensive library of corrosion samples. These samples were produced in the corrosion tank at ISU and included a large number of corroded regions in aircraft skin. The depth of the corrosion was varied to range from 1% to 50% with areas ranging from 0.25 cm^2 to 5.0 cm^2 . The plates were then assembled into various structures. The amount of metal loss was measured with calibrated x-ray thickness gauging. Each of the samples was radiographed using a microfocus setup at 10X magnification. The resulting radiographs were digitized and converted into a map of remaining metal.

Accomplishments and New Findings:

A quantitative analysis module was developed and validated for the detection of hidden corrosion in aircraft panels using the PEC instrument. This analysis module was successfully tested in AF blind trials for the detection of corrosion and its quantitative analysis capabilities was demonstrated at several ALC's.

Pulsed Eddy-Currents:

Theory:

- Developed quantitative theory for the "forward" response of the PEC instrument based on first-principles treatment of the problem starting with Maxwell's equations.
- Developed quantitative "inverse" method that estimates the location and thickness of hidden corrosion.
- Developed a novel perturbation method for PEC instrument's response to pitting corrosion.
- Developed time-domain methods for distinguishing the effects of corrosion from interfering signals such as fasteners or other support structure.

Experiment:

- Made quantitative measurements with PEC instrument on laboratory specimens designed mimic the effects of corrosion.
- Tested the accuracy of the "forward" theoretical calculations and obtained excellent agreement.
- Constructed a new portable instrument to detect wall-loss in lap-splices under AFOSR funding based on a "lunch-box" portable PC
- Incorporated theoretical inverse methods based on "time-of-arrival" and obtained accurate answers.
- Demonstrated the ability to use time-domain information to distinguish hidden corrosion from interfering signals from fasteners and support structure.
- Successfully completed AF sponsored blind trials for corrosion detection.
- Demonstrated quantitative capability of portable instrument at ALC's
- Licensed PEC instrument to Sierra Matrix, Inc.

Energy Resolved X-rays:

- Evaluated use of isotope source in backscatter imaging - flux too low for useful times
- Constructed and tested a backscatter camera use CdTe solid state detectors
- Developed x-ray tube beam monitor and adapted camera for tube mounting
- Demonstrated energy dispersive backscatter measurement of corrosion in skin to 5% metal loss
- Developed a backscatter simulation model, source collimation, detector collimation, scattering mechanism, CAD part representation, scan generation
- Fabricated and characterized a large number of engineering corrosion samples
- Improved speed of energy dispersive data analysis by a factor of 140.
- Demonstrated the use of compact room temperatures energy dispersive detectors, CdTe and CdZnTe

Personnel Supported:

Principal Investigator: James H. Rose

Principal Investigator: John C. Moulder
Student: William Ward

Principal Investigator: Joseph N. Gray
Other Investigator Terrence Jensen
Student: Brian Hinzie

Transitions

The pulsed eddy-current instrument has been licensed for production to Sierra Matrix, Inc. of Fremont CA. The contact people are John Carruthers (510-623-3690) and the president of the company, Marv Flemming.

J. C. Moulder received funding for technology transfer of the pulsed eddy-current instrument from the FAA. The enabling research was the AFOSR task and prior work for the FAA. The contact individual at the FAA is Chris Smith.

New discoveries, inventions or patent disclosures:

A record of invention has been filed for the pulsed eddy-current instrument. This is the first step in seeking patent protection for this new instrument.

An energy-dispersive x-ray backscatter camera was invented and constructed.

Documents published in whole or in part with support of this grant.

1. Radhika Satveli, *Software modeling for flaw characterization of metals through eddy-currents*, Master's Thesis, Iowa State University, 1995.
2. Radhika Satveli, John C. Moulder, Bing Wang and James H. Rose, "Impedance of a coil near an imperfectly layered metal structure: The layer approximation", *J. Appl. Phys.*, **79**, 2811 (1996).
3. Cheng-Chi Tai, James H. Rose and John C. Moulder, " Thickness and conductivity of metallic layers from pulsed eddy-current measurements", *Rev. Sci. Instrum.* **67**, (1996).
4. James H. Rose, Erol Uzal and John C. Moulder, "Pulsed eddy-current characterization of corrosion in aircraft lap splices: Quantitative modeling", *SPIE Proceedings* **2160**, 164 (1994).
5. J. C. Moulder, J. A. Bieber, W. W. Ward III and J. H. Rose, " Scanned pulsed eddy-current instrument for non-destructive inspection of aging aircraft", in *Nondestructive Evaluation of Aging Aircraft, Airports, and Aerospace Hardware*, *SPIE Proceedings* **2945**, 1, 1996.
6. Jay A. Bieber, Sunil K. Shaligram, James H. Rose and John C. Moulder, "Time-gating of pulsed eddy-current signals for depth discrimination, Review of Progress in Quantitative NDE, **16** (in press).
7. J. C. Moulder, Jay A. Bieber, William W. Ward III, Sunil K. Shaligram and James H. Rose, "Scanned pulsed-eddy-current technique for characterizing hidden corrosion and cracking in airframes", *Review of Progress in Quantitative NDE*, **16** (in press).
8. Radhika Satveli, John C. Moulder, "Eddy-current detection of pitting corrosion in aircraft lap-splices", *Review of Progress in Quantitative NDE*, **15** 1755 (1996).
9. Cheng-Chi Tai, James H. Rose and John C. Moulder, " Thickness and conductivity of metallic layers from pulsed eddy-current measurements", *Review of Progress in Quantitative NDE*, **15** 409 (1996).
10. John C. Moulder, Mark W. Kubovich, Erol Uzal and James H. Rose, " Pulsed eddy-current measurements of corrosion-induced metal loss: Theory and experiment", *Review of Progress in Quantitative NDE*, **14**, 2065 (1994).
11. B. Hinzle, *X-ray Energy Dispersive Measurements: Applications to Corrosion*, MS Thesis ISU 1996 (in preparation)
12. T.Jensen and J.Gray, " Material Thickness Measurements Using Compton Backscatter ", *Review of Progress in Quantitative Nondestructive Evaluation*, Vol. 12a, ed. by D. O. Thompson and D. E. Chimenti, Plenum Publishing Co., p.303, (1993).
13. J.Ting, T.Jensen, and J.Gray, " Using energy Dispersive X-ray Measurements for Quantitative Determination of Material Loss due to Corrosion ", *Review of Progress in Quantitative Nondestructive Evaluation*, Vol. 12b, ed. by D. O. Thompson and D. E. Chimenti, Plenum Publishing Co., p.1963, (1993).

14. J. Gray, T. Aljundi, and A. Turnbull, "Optimizing Compton Backscatter Parameters Using a Simulation Code", "Review of Progress in Quantitative Nondestructive Evaluation", vol 14A, p 369, Eds. D. Thompson and D Chimenti, Plenum Press, New York, 1995

15. D. K. Hsu, B. Patton, V. Dayal, B. Hinzie, and J. N. Gray. "Quantitative Measurement of Metal Loss Due to Corrosion in Aluminum Aircraft Skin" by, "Review of Progress in Quantitative Nondestructive Evaluation", Vol. 15B, pages 1725-1732; Eds. D. Thompson and D Chimenti, Plenum Press, New York, 1996